

PRODUCT DATA SHEET

Steel Slag 14mm Asphalt Aggregate

Product Code: SFS514

Definition

Steel furnace slag is the non-metallic product consisting essentially of calcium silicates with fused oxides of iron and, aluminium that is developed in a molten condition simultaneously with steel in a basic oxygen furnace.

The material is produced in a molten condition simultaneously with steel in a basic oxygen furnace and is a predominantly crystalline, solid rock-like material.

Description

Steel slag is dug, crushed and screened into single size aggregates.

Applications

- ◆ Asphalt Aggregate
- ◆ Filter material

Advantages

- ◆ Interlocking particle shape
- ◆ Resistant to weathering
- ◆ Strong adhesion with binders
- ◆ High skid resistance
- ◆ High stability
- ◆ High durability
- ◆ Improves resistance to rutting and deformation
- ◆ Good flow properties
- ◆ Resistant to stripping
- ◆ Well graded
- ◆ Strong load bearing capacity
- ◆ Effective utilisation of an industrial by-product conserving natural resources

Typical Grading

SIEVE	% PASSING
19.0 mm	100
13.2 mm	78
9.5 mm	24
6.7 mm	5
4.75 mm	2
2.36 mm	2
1.18 mm	1

Typical Physical Properties

Particle Density – SSD	3.47 t/m ³
– Dry	3.40 t/m ³
Water Absorption	1.8 %
Free Lime	2.5 %
Particle Shape (2:1)	3
Los Angeles Value	16
Dry Strength	286 kN
Wet Strength	269 kN
Dry/Wet Variation	6 %
Sodium Sulphate Soundness	0.3
Polishing Agg. Friction Value	62
Resistance to Stripping	93

Technical Services and Customer Enquiries

Marketing Department
 Australian Steel Mill Services Pty
 21 Processing Area
 Springhill Road
 PORT KEMBLA NSW 2505

Telephone: (02) 4255 1125
 Facsimile: (02) 4276 2369

