

PRODUCT DATA SHEET

Steel Slag 20mm Asphalt Aggregate

Product Code: SFS520

Definition

Steel furnace slag is the non-metallic product consisting essentially of calcium silicates with fused oxides of iron and, aluminium that is developed in a molten condition simultaneously with steel in a basic oxygen furnace.

The material is produced in a molten condition simultaneously with steel in a basic oxygen furnace and is a predominantly crystalline, solid rock-like material.

Description

Steel slag is dug, crushed and screened into single size aggregates.

Applications

- ◆ Asphalt Aggregate
- ◆ Filter material

Advantages

- ◆ Interlocking particle shape
- ◆ Resistant to weathering
- ◆ Strong adhesion with binders
- ◆ High skid resistance
- ◆ High stability
- ◆ High durability
- ◆ Improves resistance to rutting and deformation
- ◆ Good flow properties
- ◆ Resistant to stripping
- ◆ Well graded
- ◆ Strong load bearing capacity
- ◆ Effective utilisation of an industrial by-product conserving natural resources

Typical Grading

SIEVE	% PASSING
26.5 mm	100
19.0 mm	87
13.2 mm	22
9.5 mm	7
6.7 mm	3
4.75 mm	2
2.36 mm	2
1.18 mm	2

Typical Physical Properties

Particle Density – SSD	3.33 t/m ³
– Dry	3.28 t/m ³
Water Absorption	1.5 %
Free Lime	2.7 %
Particle Shape (2:1)	1
Los Angeles Value	15

Technical Services and Customer Enquiries

Marketing Department
 Australian Steel Mill Services Pty
 21 Processing Area
 Springhill Road
 PORT KEMBLA NSW 2505

Telephone: (02) 4255 1125
 Facsimile: (02) 4276 2369

