



PRODUCT DATA SHEET

6mm Concrete Sand

Product Code: ABF 206

Definition

Blast furnace slag is the non-metallic product consisting essentially of silicates and aluminosilicates of calcium and other bases, which is developed in a molten condition simultaneously with iron in a blast furnace.

Air-cooled blast furnace (ABF) slag is a predominantly crystalline, solid rock-like material.

Typical Grading

SIEVE	% PASSING
9.5mm	100
6.7	99
4.75	90-100
2.36	65-75
600µm	25-40
75	3-7

Description

Crusher dust is a grey coloured fine aggregate consisting of angular to roughly cubical shaped particles with a characteristically vesicular structure and rough surface texture.

Applications

Coarse sand for concrete and masonry

Properties

- ◆ Resistant to heat and fire
- ◆ Alkaline in presence of moisture
- ◆ Non-plastic
- ◆ Consistent chemistry
- ◆ Excellent load bearing capacity
- ◆ High stability and durability
- ◆ Ease of compaction

Typical Physical Properties

Maximum Dry Density	2.00-2.15 t/m ³
Optimum Moisture	10-13%
Bulk Density (Loose)	1.35-1.45 t/m ³
(Compacted)	1.50-1.60 t/m ³
Particle Density (Dry)	2.70-2.80 t/m ³
(SSD)	2.75-2.85 t/m ³
Water Absorption	2.5-3.5%
Plasticity Index	Non-plastic
Organic Impurities	Free
Sugar	Free
pH	10-12

Technical Services and Customer Enquiries

Telephone: (02) 4255 1178

Email: enquiries@asms.com.au

Website: www.asms.com.au

ASMS Disclaimer

The information contained in this Product Data Sheet while accurate for general consideration, no warranty is expressed or implied regarding the accuracy of this data on specific applications. Information is furnished upon the condition that the user shall obtain specific advice and/or carry out tests to determine suitability for a particular purpose and for specific site and application conditions.

Sales specifications, although current at the time of publication, are subject to change due to process improvements. For the latest product specifications or usage updates contact ASMS.