

# CONCRETE SAND

## Product Code: ABF206

### PRODUCT DESCRIPTION

**ASMS ABF206 is a 6x0 mm coarse concrete sand.**

### APPLICATIONS

**ABF206** is suitable for use in a range of civil and manufacturing applications including:

- Concrete
- Masonry raw material

### COMPOSITION AND MATERIALS

**ABF206** is produced from blast furnace slag by crushing, screening and processing to remove all single size aggregates. The fines are screened off to yield a grey coloured fine aggregate concrete sand consisting of angular to roughly cubical shaped particles with a characteristically vesicular structure and rough surface texture.

Blast furnace slag is the non-metallic product consisting essentially of silicates and aluminosilicates of calcium and other bases developed in a molten condition simultaneously with iron in a blast furnace.

Air-cooled blast furnace slag is a predominantly crystalline, solid rock-like material.

### ADVANTAGES

- Consistent chemistry
- Excellent load bearing capacity
- Non-plastic
- Resistant to heat and fire
- Alkaline in presence of moisture
- Effective utilisation of an industrial by-product conserving natural resources

### TYPICAL GRADING

SIEVE	% PASSING
9.5 mm	100
6.7 mm	99
4.75 mm	90
2.36 mm	60
600 µm	25
75 µm	6

### TYPICAL PHYSICAL PROPERTIES

PROPERTY	UNIT	TYPICAL
Bulk Density (Loose)	t/m <sup>3</sup>	1.3-1.5
Bulk Density (Compacted)	t/m <sup>3</sup>	1.5-1.7
Particle Density (Dry)	t/m <sup>3</sup>	2.6-2.8
Particle Density (SSD)	t/m <sup>3</sup>	2.7-2.9
Water Absorption	%	3-6
Plasticity Index	-	Non-Plastic
Organic Impurities	-	Free
pH	-	10-12

### TECHNICAL AND CUSTOMER ENQUIRIES

Telephone: (02) 4255 1125

Email: [enquiries@asms.com.au](mailto:enquiries@asms.com.au)

#### ASMS DISCLAIMER

The information contained in this Product Data Sheet is accurate for general consideration, however, no warranty is expressed or implied regarding the accuracy of this data on specific applications. Information is furnished upon the condition that the user shall obtain specific advice and/or carry out tests to determine suitability for a particular purpose and for specific site and application conditions. Sales specifications, although current at the time of publication, are subject to change due to process improvements. For the latest product specifications or usage updates contact ASMS. PDS-ABF206: Rev. 8: 13.05.15