

PRODUCT DATA SHEET

80/20 SLAG ROAD BASE

Product Code: RBU800

PRODUCT DESCRIPTION

ASMS RBM800 is a high quality self-cementing Road Base.

APPLICATIONS

ASMS RBU800 is used in a variety of rigid pavement applications requiring slow setting characteristics.

COMPOSITION AND MATERIALS

RBU800 is a blend of graded air-cooled blast furnace slag and granulated blast furnace slag in nominally 80/20 volumetric proportions.

Blast furnace slag is the non-metallic product consisting essentially of silicates and aluminosilicates of calcium and other bases developed in a molten condition simultaneously with iron in a blast furnace.

Air-cooled blast furnace slag is a predominantly crystalline, solid rock-like material. Granulated blast furnace slag is a glassy, granular product.

ADVANTAGES

- Inherent cementitious properties.
- Interlocking particle shape.
- Ease of compaction.
- Advantageous placement working life.
- Long term strength gain.
- Lower tonnage required per cubic metre.
- Potential to reduce asphalt layer thickness in selected applications.
- Effective utilisation of an industrial by-product conserving natural resources.

TYPICAL GRADING

SIEVE	% PASSING
26.5 mm	100
19.0 mm	95 – 100
13.2 mm	70 – 90
9.5 mm	60 – 80
2.36 mm	30 – 50
425 µm	10 – 25
75 µm	4 – 12

TYPICAL PHYSICAL PROPERTIES

PROPERTY	UNIT	TYPICAL
Maximum Dry Density	t/m ³	1.9 – 2.1
Optimum Moisture	%	11 – 14
Misshapen Particles (2:1)	%	5 – 20
Dry Strength	kN	75 – 110
Wet Strength	kN	70 – 105
Wet/Dry Variation	%	6 – 12
Acid soluble Sulfate, SO ₃	%	0.3 – 0.6
Liquid Limit	%	n/a
Plastic Limit	%	n/a
Plasticity Index	-	Non Plastic
Modified Texas Triaxial	-	2.0 – 2.5
UCS (7 days acc.)	MPa	0.5 – 1.5

TECHNICAL AND CUSTOMER ENQUIRIES

Telephone: (02) 4255 1100

Email: enquiries@asms.com.au

ASMS DISCLAIMER

The information contained in this Product Data Sheet is accurate for general consideration, however, no warranty is expressed or implied regarding the accuracy of this data on specific applications. Information is furnished upon the condition that the user shall obtain specific advice and/or carry out tests to determine suitability for a particular purpose and for specific site and application conditions. Sales specifications, although current at the time of publication, are subject to change due to process improvements. For the latest product specifications or usage updates contact ASMS. PDS-RBU800: Rev. 6: 03.04.25 1/1